

PREMIUM RESIN TECH.

3605 - 32nd Street., Port Huron, MI 48060
(586) 530-3633 RandDResin.com

Clear Room Temperature Laminating System

RDR-3410 / RDH-9386-99

MIXING RATIO: 100 : 33PBW

This clear, unfilled all-purpose clear epoxy resin system with a long pot life. **RDR-3410 / RDH9386-99** has strong impact and chemical resistance and excellent wetting qualities.

TYPICAL PHYSICAL PROPERTIES

Color	Clear
Pot Life @ 72° F (200g mass)	60 minutes
Ratio by Weight	100 pbw to 33 pbw
Flexural Strength @ 72° F	12,500
Flexural Modulus @ 77° F	40,900
Density:	
Resin	9.7
Hardener	7.9
Mixed	9.1
Heat Deflection	200 °F
Hardness, Shore "D" @ 72° F	80
Shelf Life Resin / Hardener	1 year
Cure Time	24 hours

The information herein is accurate to the best of our knowledge. Premium Resin Tech., assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of suitability of any material is the sole responsibility of the user. All material may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards which exist.