



HEXCEL HEXFORCE FIBERGLASS E-GLASS PLAIN WEAVE STYLE 7544 F16 FINISH MODEL #: F-1624-50

HEXFORCETM 284 ZB PRIME TEX®

Type of Yarns (US System / SI Units)

Warp Yarn: ECG 37 1/2 / EC9 134 x2

Fill Yarn: ECG 37 1/4 / EC9 134 x4

Fabric Weight, Dry (US System / SI Units)

18.00 oz/yd² / 610 g/m²

Weave Style

2 End Plain Weave

CONSTRUCTION

Nominal Construction (US System / SI Units)

Warp Count: 28/in / 11.02/cm

Fill Count: 14/in / 5.51/cm


Fabric Thickness (US System / SI Units)

19.10 mil / 0.49 mm

Breaking Strength

Warp: 700 lbf/in

Filling: 700 lbf/in



Information and data included in this data sheet is considered to be accurate and reliable to the best of our knowledge however it is not guaranteed to be so. It is the user/buyer's responsibility to determine for themselves the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary. Composite Envisions make no representations or warranties as to the results to be obtained in using any material. As Composite Envisions cannot foresee all conditions under which products will be used, user/buyer waives any claim against Composite Envisions for direct, indirect, consequential, or exemplary damages including without limitation, damage which may incur as a result of user/buyer's use or misuse of the product or the product's failure to perform to any expected performance level.

Composite Envisions LLC
8450 Development Court
Wausau, WI 54401 USA
+1 715-842-0101
info@compositeenvisions.com
<https://compositeenvisions.com/>



COMPOSITE ENVISIONS