



HexForce™ 1597

Glass Fabric

Product Data

Style 1597		US System	SI Units
Type of Yarns	Warp Yarn:	ECG 37 1/4	EC9 134 x4
	Fill Yarn:	ECG 37 1/4	EC9 134 x4
Fabric Weight, Dry		38.57 oz/yd ²	1308 g/m ²
Weave Style	Triple Plain		

Construction

Nominal Construction	Warp Count:	30/in	11.81/cm
	Fill Count:	30/in	11.81/cm
Fabric Thickness		37.80 mils	0.96 mm
Breaking Strength	Warp	1300 lbf/in	
	Filling	1400 lbf/in	

Important

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.

For More Information

Hexcel is a leading worldwide supplier of composite materials to aerospace and other demanding industries. Our comprehensive product range includes:

- Carbon Fiber
- Reinforced Fabrics
- Carbon, Glass, Aramid and Hybrid Prepregs
- RTM Materials
- HexTOOL® composite tooling material
- Structural Film Adhesives
- Honeycomb Cores
- Engineered Core

1913 North King Street

Seguin, Texas 78155

Phone: 830-379-1580

Fax: 830-379-9544

Customer Service Toll Free: 1-866-601-5430

For European sales office numbers and a full address list, please go to:

<http://www.hexcel.com/contact/salesoffices>

Copyright © 2014 – © Hexcel and Hexcel logo are registered trademarks of Hexcel Corporation, Stamford, Connecticut.
™ HexForce is a trademark of Hexcel Corporation, Stamford, Connecticut.

June 2014

