

DATA SHEET
STRETCHLON®
 Highest Flexibility of Any Bagging Film

MECHANICAL	Unit	Test Method	SL 200 ⁽¹⁾	SL 700 ⁽¹⁾	SL 800	SL 850
				(Sheeting/Tubing)	(Sheeting)	(Tubing)
Elongation at break	>%	ASTM D 882	500	500	450	450
Tensile strength	>psi	ASTM D 882	8,000	6,500	10,000	12,000
	>N/mm ²		55	45	69	82
THERMAL						
Maximum recommended use temperature ⁽²⁾	°F		250	385	400	400
	°C		121	195	204	204
Melt point by DSC	°F	ASTM D 3418	N/A	395	410	417
	°C		N/A	202	210	214
CHEMICAL						
Materials to avoid:			Note 3	Note 3	Strong Oxidizers/ Phenol Compounds ⁽⁴⁾	
PHYSICAL						
Density	g/cm ³	ASTM D 792	1.10	1.23	1.14	1.14
Yield	in ² /#/mil		21,600	22,503	24,280	24,280
	m ² /kg/25µm		30.6	31.9	34.5	34.5
Color			Green	Cream	Orange	Orange
Shelf Life	Months		18	18	18	18
Forms Available ^(5,6) :	mil		1.5	3	2	2
	µm		37.5	75	50	50
			Sheeting	Sheeting	Sheeting	Layflat
			Centerfold	Centerfold		Tubing
			Layflat Tubing			

- NOTES:
- (1) Sale and use of the product covered by US Patent No. 5,123,985.
 - (2) Maximum recommended use temperature is dependant upon the duration at maximum temperature and is process specific. Airtech recommends testing prior to use.
 - (3) Stretchlon 700 is recommended for phenolic and epoxy resins. Stretchlon 700 are not recommended for BMI, Polyester, or Vinylester resins.
 - (4) Stretchlon 800 and 850 are recommended for epoxies and BMI resins. Stretchlon 800 and 850 are not recommended for phenolic resins.
 - (5) Customer manufactured shapes are available to fit your individual requirements.
 - (6) Other gauges are available upon request. Minimum order required. Consult the dimension chart in this section for dimensional information. Please consult Airtech for further information.

CATALOG POSITION: **BAGGING FILMS**

As the conditions or methods of use are beyond our control, Airtech International, Inc. does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech International, Inc. disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes.

MORE THAN A MANUFACTURER...A TECHNICAL PARTNER!

