

PREMIUM RESIN TECH.

4645 BREE Rd., EAST CHINA, MI 48054
(586) 530-3633 RESIN333@AOL.COM

HIGH TEMPERATURE BLACK SURFACE COAT

**RDR-1902 / RDH-
9302, RDH-9106**

Resin / Hardener(s)

MIXING RATIO: 100:16

RDR-1902 is a high gloss, chemical resistant, high heat surface coat. RDR-1902 system is the recommended surface coat for use with high temperature laminating.

TYPICAL PHYSICAL PROPERTIES

Used w/:	RDH-9302	RDH-9106
Color	Black	Black
Pot Life @ 72° F (200g mass)	14 minutes	60 minutes
Viscosity	gel	gel
Ratio by Weight	100 pbw to 15 pbw	100 pbw to 15 pbw
Flexural Strength @ 72° F	15,000 psi	16,000 psi
Tensile Strength	9,500 psi	10,000 psi
Compressive Strength	15,000 psi	16,000 psi
Heat Distortion	350°F	350°F
Hardness, Shore "D" @ 72° F	90	90
Shelf Life Resin / Hardener	1 year	1 year
Machinability	poor	poor
Cure Schedule	24 hours	24 hours

Recommended Post Cure: If tool is used at high temperature. Upon Completion, the tool should be allowed to cure at ambient temperature for 24 hrs. Post cure cycle should be 50 degrees per hour (Tool Temperature, not air Temperature). Not more than 5 degrees per min.

The information herein is accurate to the best of our knowledge. Premium Resin Tech., assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of suitability of any material is the sole responsibility of the user. All material may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards which exist.