



DUNAPOL® C 035 HL

Rev. N°4 - Date 05/12/2017

Description

Two-component polyurethane system suitable to obtain a rigid foam

Blowing agents: CO₂

Typical characteristics – Polyol

Component Name			Polyol
Density (77°F, 25°C)	ASTM D891	lb/ft ³ (g/l)	DUNAPOL® C 035 HL 66.8-69.3 (1070-1110)
Viscosity (77°F, 25°C)	ASTM D2196	P (mPa s)	6.8-7.8 (680-780)
Storage temperature		°F (°C)	50-86 (10-30)
Shelf Life		Months	6
Appearance			Light yellow liquid

Typical characteristics - Isocyanate

Component Name			Isocyanate
Density (77°F, 25°C)	ASTM D891	lb/ft ³ (g/l)	DUNAPOL® A 310 74.9-77.4 (1200-1240)
Viscosity (77°F, 25°C)	ASTM D2196	P (mPa s)	1.8-2.6 (180-260)
Storage temperature		°F (°C)	50-95 (10-35)
Shelf Life		Months	6
Appearance			Brown liquid

Mixing Ratio

Mixing ratio by weight POL/ISO	parts	100/130
Mixing ratio by volume POL/ISO	parts	100/115

Typical characteristics of reaction

Components temperature		°F (°C)	70 (21)
Mixing time		h min' sec"	30"
Cream time		h min' sec"	35"-45"
Gel time		h min' sec"	3'00"-3'40"
Free rise density	EN 1602/ASTM D1622	lb/ft ³ (kg/m ³)	2.3-2.5 (36,5-39,5)

Characteristics of the polymer (int.procedure DU/25)

Applied density	EN 1602/ASTM D1622	lb/ft ³ (kg/m ³)	3.4 (55)
Compressive strength - Average	EN 826/ASTM D1621	psi (kg/cm ²)	39.6 (2,78)
Closed-cell content	EN ISO 4590/ASTM D6226	%	>92
Thermal conductivity – Initial (68°F, 20°C)	EN 12667/ASTM C518/ASTM C177	BTU·in/hr·ft ² ·°F (W/mK)	0.17 (0,0247)
Fire reaction (maximum extent of burnt length)	EN ISO 3582	in (mm)	2.4 (<60)
Fire reaction (extinguishing time)	EN ISO 3582	s	<120



DUNAPOL® C 035 HL

Rev. N°4 - Date 05/12/2017

Handling notice

In order to obtain the best results, thermostatic conditioning of components is essential.

Data coming from tests performed in laboratory, with components at the indicated temperature; manual mixing with a mechanical mixer at 1500-2500 rpm, in free rise in box/glass or in closed mold at the suggested temperature.

Wherever possible apply products in ventilated areas, wearing gloves, protective eyewear, barrier creams and suitable protective clothes.

Avoid contact with unhardened materials.

In case of accidental contact with the skin, wash with lukewarm water and soap for at least 10 minutes. Do not wash affected areas with solvents as this may increase contamination.

In some applications polyurethane may present fire risks, e.g. if exposed to fire or to excessive heat in presence of oxygen or air, including when welding or cutting with torches.

Lifetime of products is referred to materials stored in sealed containers in dry rooms, at recommended temperatures and protected from direct sunlight. Expiry is printed on packaging.

It is the Customer's responsibility to determine if product described herein is appropriate for Customer's purposes and end-use and to ensure that working place, storage and disposal practices are in compliance with any applicable law.

Remarks

For usage information, personal protective equipment, transport, storage and disposal of waste it is essential to refer to the Material Safety Data Sheets.

Values shown are determined from laboratory tests and obtained under controlled conditions; they outline typical characteristics and they do not constitute anyhow a sales specification; they are based on DUNA-USA's current knowledge and experience of the products when properly stored, handled and applied in accordance with our recommendations.

This Technical Data Sheet cancels and replaces any other previous issue.

DUNA-USA Inc. does not accept any responsibility for incorrect use of its products as it cannot ensure the correct methods of application have been followed; we therefore specifically disclaim any liability for consequential or incidental damages of any kind, including lost profits.

DUNA-USA Inc. reserves the right to change the data in this information sheet without any prior notice.
